

1 TOPCOATED ADHESIVE

2 This invention relates to pressure-sensitive adhesive
3 tapes, adhesive tabs formed therefrom, and methods for
4 manufacturing the same. In one aspect, the invention relates
5 to improvements in transfer tapes and like products, and in
6 the manufacture of the same. In another aspect, the invention
7 relates to improvements in laminate web constructions of
8 diaper fastener-tab stock of the kind adapted to be supplied
9 to a diaper manufacturer and to be separated by the
10 manufacturer into individual diaper-fastening tabs and applied
11 to individual diapers, usually two tabs to a diaper for infant
12 diapers and six tabs to a diaper for adult diapers. In this
13 aspect, the invention particularly relates to means forming
14 part of the diaper tabs and providing novel conveniently
15 manipulated fingerlifts for the tabs.

16 Prior Art

17 It has been previously proposed to make articles from
18 pressure-sensitive adhesive tapes in which the layer of
19 pressure-sensitive adhesive is partially covered with a
20 printed pattern of ink.

21 In U.S. Patent 3,159,930 to Allen et al., a pressure-
22 sensitive tape has a layer 5 printed on the adhesive face.
23 This layer combines adhesive masking and indicia functions,
24 the indicia being in the form of negative images in the mask.
25 The masking layer masks most of the adhesive at the centers
26 of the document-containing articles which are to be cut from
27 the tape, but leaves the adhesive exposed at the edges of the
28 articles. The tape is combined with a release liner.

29 In U.S. Patent 3,874,893 to Cherrin, which is similar
30 to Allen et al., one or more layers of ink or "overprint
31 lacquer" or "a coating which through solvent or other action
32 causes the adhesive to lose most of its adhesive properties"

1 are applied to the adhesive side of a tape using a
2 flexographic press. When two printed layers are used, the
3 first consists of printed indicia and the second of a
4 background layer which is patterned to leave the adhesive
5 exposed at the edges of document-containing articles which are
6 to be cut from the tape. The background layer functions to
7 mask the adhesive so as to render it non-adhesive at the
8 printed areas. In one embodiment, additional spaced patterns
9 56 (Figs. 12 and 13) are printed on the adhesive to function
10 as corner lift tabs when the tape is cut into individual
11 articles. However, the great majority of the cutting of the
12 tape is done directly through the adhesive at unprinted areas
13 thereof, thereby leaving unprinted adhesive directly exposed
14 at the side edges of the tape.

15 In U.S. Patent 4,068,028 to Samonides, indicia are
16 printed on the adhesive layer of transparent pressure-
17 sensitive labels. These indicia are visible but "buried" and
18 protected when the labels are applied to a mounting surface.
19 In a variant, the labels are opaque, and indicia are printed
20 both on the adhesive layer and on the face side of the label.
21 When the label is mounted on the inner side of a glass window
22 or the like, the indicia on the adhesive side are visible from
23 the exterior side of the window and the indicia on the face
24 side are visible from the interior side.

25 In U.S. Patent 4,107,811 to Imsande, a tacky floor mat
26 consists of a stack of adhesive-coated sheets peelably joined
27 to each other. To provide lift tabs for the sheets, "a thin
28 coating of non-adhesive material 18 is print-deposited" (col.
29 3, line 61) in a pattern on the adhesive-coated web material
30 from which the sheets are to be cut. The adhesive-coated web
31 material with the patterned coating 18 thereon is then
32 laminated to itself to form a multilayer web (presumably with
33 the pattern of non-adhesive material 18 maintained in
34 register, layer to layer). The laminated material is then cut
35 to sheet size in such manner that the patterned non-adhesive
36 material 18 ends up at the corners of the stacked sheets.

1 non-adhesive material may be of a different color than the
2 sheets.

3 In U.S. Patents 4,671,003 and 4,787,158 to Vitol,
4 removable pressure-sensitive sign stock is backed with release
5 liner which has been perforated at regular intervals, the
6 perforations being in the form of round openings where the
7 adhesive is exposed. Talc or other adhesive masking material
8 is applied to the adhesive at the areas of these openings, and
9 the stock is then slit in both directions to form individual
10 signs of rectangular or other shape each having one or more
11 starting tabs at one, two or four corners. Circular labels
12 are also disclosed having wedge-shaped non-adhesive areas, but
13 how the corresponding perforations in the liner relate to the
14 circular label shape, and how the circular labels are formed
15 from the label stock is not apparent.

16 Various fingerlift arrangements specific to diaper tabs
17 are also known in the prior art. One simple arrangement is
18 to provide an adhesive-free zone at the fingerlift edge, as
19 in U.S. Patent 3,833,456 to Reed et al. This fingerlift edge
20 can be difficult to grasp; there is no clear indication of the
21 presence of a fingerlift, and the unsupported edges of rolls
22 from which such tabs are cut can be easily damaged.

23 Another fingerlift arrangement for a diaper tab is a
24 fold-over arrangement, as in U.S. Patent 3,893,460 to Karami.
25 If such folding-over is done during manufacture of the diaper
26 fastener stock, differences in thickness are created across
27 the width of the stock, causing distortions when the stock is
28 rolled up for storage and shipment. On the other hand, if the
29 folding-over is delayed only to be attempted on the diaper
30 line, the difficulty of performing that step as part of the
31 fastener dispensing and application procedure on the diaper
32 line presents a risk of line stops and delays in diaper
33 production.

34 Another known fingerlift arrangement for a diaper tab
35 is a strip lamination, as in U.S. Patent 4,726,971 to Pape
36 et al. The laminated strip extends outwardly of the width

1 of the diaper fastener stock, so that when the same is rolled
2 and transported, the laminated strip can be easily damaged.
3 Also, the strip creates local thickness variations in the
4 roll.

5 Still another arrangement is a pull string, as in U.S.
6 Patent 4,005,713 to Mesek. This too may cause thickness
7 variations, and may be complicated to fabricate and
8 manipulate, particularly at high diaper line speeds.

9 Summary of the invention

10 Like the first six prior-art references listed above,
11 the present invention also involves the making of articles
12 from pressure-sensitive adhesive tapes in which the layer of
13 pressure-sensitive adhesive is partially covered with a
14 printed pattern of an adhesive barrier or ink. However, in
15 the present invention as it relates to transfer tapes, the
16 printing is along a continuous zone or line, and the tape is
17 formed in whole or in part by slitting along that continuous
18 line through the tape substrate, an adhesive coating, and the
19 printed barrier. In the present invention as it relates to
20 diaper tabs, an adhesive barrier or ink is used to form end
21 fingerlifts for the tabs.

22 In one aspect, the present invention involves the concept
23 of utilizing such means to eliminate or minimize
24 complications, constraints and disadvantages involved in
25 pattern-coating substrates with pressure-sensitive adhesive
26 in the manufacture of transfer tapes and other articles. In
27 particular, the invention minimizes or eliminates
28 complications, constraints and disadvantages involved in the
29 need to pattern-coat the adhesive as it is applied in order
30 to allow slitting at one or more intermediate locations across
31 the width of the line to define a specific tape width or
32 widths, and in order to provide adhesive-free and therefore
33 "pick"-free roll edges.

34 The invention overcomes the present inability to slit

1 rolls of premanufactured transfer tape stock to various widths
2 on demand, and eliminates the corresponding need to
3 manufacture and inventory various widths of transfer tape
4 pending demand for one or the other specific width or widths.
5 The invention enables the manufacture of tape stock and tapes
6 of substantially uniform thickness from one edge to the other,
7 with attendant advantages to the manufacturer and converter.

8 In another aspect, the invention provides for the
9 manufacture of diaper fastener-tab stock, and diaper fastening
10 tabs formed from such stock, in a manner compatible with
11 current diaper manufacturing practice, providing improved
12 diaper tabs, and improved tabbed diapers, at little or no
13 increase in costs over the practices of the prior art.

14 In this respect, the present invention provides diaper
15 tab fasteners having fingerlifts (i.e., end tabs for the tab
16 fasteners themselves) which are "built-in," which are easy and
17 convenient to use, which overcome the problems of the prior-
18 art diaper tab fingerlifts listed above, and which offer new
19 advantages including the ability to economically provide
20 improved distinguishability of the fingerlifts from the
21 remainder of the tabs, the ability to provide for the
22 absorption of finger oils or other contaminants, and the
23 ability to add fragrances to the tabs.

24 *Ans. A27* In respect of the manufacture of diaper fastener-tab
25 stock with "built-in" end tabs, the invention provides a
26 variant or alternative to the design of diaper fastener-tab
27 with built-in end tab taught in U.S. Patent Application Serial
28 No. 07/710,692, filed June 5, 1991, of common assignee.

29 Detailed Description

30 The features and advantages of the invention will be
31 more fully understood from the following description of
32 specific examples, together with the drawings, in which:

33 FIG. 1 is a schematic isometric view illustrating certain
34 prior art coating and slitting practices.

1 FIGS. 2 and 3 are similar views illustrating coating and
2 slitting practices according to the present invention.

3 FIG. 4 is a broken cross-sectional view taken along plane
4 4-4 in FIG. 2, and inverted 180 degrees.

5 FIG. 5 is a cross-sectional view of an individual tape
6 slit from the stock of FIG. 4.

7 *INS. A3* FIG. 6 is a cross-sectional view of two layers of a roll
8 of the tape seen in FIG. 5.

9 FIG. 7 is a cross-sectional view similar to FIG 5 and
10 showing tape stock for the manufacture of diaper tabs
11 according to the invention.

12 FIG. 8 is a view similar to FIG. 7 and showing additional
13 tape stock used with the stock of FIG. 7.

14 FIG. 9 is a cross-sectional view of the tape stocks of
15 FIGS. 7 and 8 combined with each other. FIG. 9 may also be
16 interpreted as a side elevation view of an individual diaper
17 tab cut from the combined stock.

18 FIG. 10 shows an individual tab corresponding to the
19 construction of FIG. 9 applied around the edge of a diaper.

20 FIG. 11 shows the same tab deployed for fastening to
21 another part of the diaper.

22 FIG. 12 is a view similar to FIG. 9 and showing a
23 different form of diaper tab embodying the invention.

24 *INS. A4* The coating and slitting shown highly schematically in
25 FIG. 1 illustrates prior practices in the manufacture of
26 transfer tape. A roll 10 may comprise a web of release liner
27 substrate 12 which is coated on both sides with release
28 coatings (not shown) either in prior coating operations before
29 the forming of roll 10 or as initial coating and drying steps
30 (not shown) following off-feed from roll 10.

31 At an adhesive-applying station A, a patterned adhesive
32 coating 14 is applied to the substrate 12. The patterning
33 results in a well-known manner from the use of die deckeling
34 or the use of pattern bars (not shown) to prevent or minimize
35 the application of adhesive along lines or zones 16 which are
36 free or relatively free of adhesive.

1 The stock with its patterned adhesive coating is then
2 slit by the slitters 18 into individual transfer tapes, and
3 self-wound to form rolls of specific widths, such as the three
4 individual rolls 21-23 in the illustration. The slitting
5 occurs along the absolutely or relatively adhesive-free lines
6 or zones 16. Slitting may also be performed at the adhesive-
7 free side edges if edge trimming is required, but slitting at
8 only the central locations is shown to simplify the
9 illustration.

10 In accordance with well-known practice, the release
11 coating (not shown) on the adhesive-carrying side of the
12 substrate 12 is chosen to give a higher or harder release
13 than the release coating (not shown) on the opposite or
14 exposed side of the substrate. When each tape is self-wound
15 into roll form, the adhesive associated with one turn of
16 substrate contacts the exposed side of the preceding turn of
17 substrate which bears the release coating which allows
18 relative low or easy release. The result is that when the
19 roll is subsequently unwound, the adhesive layer remains
20 associated with the same length of substrate on which it was
21 coated even though there is a release coating (the one of
22 relatively higher or harder release) between the adhesive and
23 that same length of substrate.

24 The adhesive face of the tape then can be applied to
25 label facestock or to another object intended to be adhesively
26 mounted in its end use, and the adhesive 14 permanently
27 adheres thereto. The substrate 12 then functions as a release
28 liner protecting the adhesive 14 until the liner is removed
29 and the label or other object is adhered to its final
30 mounting. This final removal of the liner utilizes the
31 relatively higher or more difficult release action of the
32 release coating on the adhesive-bearing side of the substrate
33 12.

34 The prior-art procedures described above and illustrated
35 in FIG. 1 in highly schematic form require that the adhesive
36 coating be patterned as it is applied in accordance with the

1 specific tape width or widths desired. This means that
2 adhesive-coated transfer tape stock cannot be premanufactured
3 and inventoried, to be slit to various widths on demand.
4 Instead, all widths expected to be eventually sold must be
5 patterned at the time the adhesive is applied, and widths of
6 various sizes then held in inventory pending eventual sale.
7 Such inventory consists of tape stock that has at least been
8 patterned to width. Slitting to width may be performed in the
9 same pass as patterning, or may be delayed up until time of
10 sale. Some widths may sell more slowly than expected, and
11 others faster, presenting the necessity of maintaining
12 whatever inventory is "thrust on" the manufacturer by reason
13 of bad guesses as to demand for various widths. For example,
14 in the example illustrated in FIG. 1, the operation
15 illustrated may be carried out as a result of an order for
16 tape of the width of roll 21, an intermediate width.

17 Relatively narrow tape roll 22 and relatively wide tape
18 roll 23 (or the patternings for such rolls when slitting is
19 performed at a later pass) result as byproducts, so to speak,
20 of the manufacture of tape roll 21 and are a product of the
21 manufacturer's best guess as to the market for tapes of
22 various sizes, and must be inventoried until tapes of those
23 specific sizes are in fact ordered.

24 Another disadvantage of prior art practice is the fact
25 that it is rather complicated to reset a coating operation
26 as required by changes in tape widths to be cut. Each change
27 requires redeckeling a die or resetting a pattern bar.

28 The relatively or absolutely adhesive-free lines or zones
29 16 present another problem in that the thickness of the stock
30 is considerably less at these zones than on the portions of
31 the stock bearing the adhesive layer 12. Thus, the stock at
32 the edges of the rolls 21-23 is substantially thinner than at
33 the central portions of the rolls, so that the stock is firmly
34 wound on itself, layer-to-layer, only at the central portions
35 and not at the edges. The stock at the edge portions is
36 therefore subject to being readily deformed and damaged by

1 accidental contact with any solid object.

2 In one aspect of the invention, these complications,
3 constraints and disadvantages of prior-art practice may be
4 largely or wholly eliminated. Thus, in the manufacture of
5 transfer tape as illustrated in FIG. 2, a roll 30 may again
6 be provided comprising a web of release liner substrate 32
7 which again is coated on both sides with release coatings
8 (not shown in this view) either in prior coating operations
9 before the forming of roll 30 or as initial coating and drying
10 steps (not shown) following off-feed from roll 30.

11 However, at the adhesive-applying station A, a layer of
12 adhesive 34 is applied to the substrate 32 continually across
13 the width of the substrate 32. The adhesive-coating step may
14 be performed in the absence of any patterning, as shown, or
15 less preferably there may be patterning at the side edges.

16 Following application of the adhesive layer 34, adhesive-
17 inhibiting masking 36 is applied at a printing station P. The
18 masking may be an ink applied with a flexographic printing
19 press or laser printer (not shown), whose positions across the
20 width of the adhesive coating 34 may be readily adjusted as
21 desired to thereby determine tape width. Preferably, the
22 masking is applied at the side edges, as shown, as well as at
23 an intermediate portion or portions of the web.

24 Following drying of the ink or masking, employing drying
25 means if required (not shown), the adhesive-coated stock is
26 then slit by the slitter 38. Slitting may also be performed
27 at the side edges if edge trimming is required, but slitting
28 at only the central location is shown to simplify the
29 illustration. The slit stock is then self-wound to form the
30 individual transfer tape roll 41, and the reserve roll 44 of
31 adhesive-coated stock. The stock in the reserve roll 44 is
32 not "committed" to specific roll widths, such as the
33 relatively narrow width of the roll 22 or to the relatively
34 wide width of the roll 23 as in the prior-art example of FIG.
35 1.

36 If, at a later time, an order is received for one of the

1 latter widths, or any other width less than that of the
2 reserve roll 44, the reserve roll can be processed as
3 illustrated in FIG. 3. Thus, the adhesive-coated reserve
4 roll 44 is unwound and passed through a printing station P
5 to receive the adhesive-inhibiting masking 36a. The lateral
6 location of the print cylinders or jets (not shown) is readily
7 adjusted to produce the masking at the desired location across
8 the width of the reserve roll 44, as opposed to the laborious
9 process of redeckeling a die or readjusting a pattern bar,
10 either of which involves resetting the coating operation.

11 Following drying of the masking, employing drying means
12 if required (not shown), the stock is then slit by the slitter
13 38a. Thus a roll 42 of narrow width is produced pursuant to
14 a specific order, and also a roll 43 which, if not sold, may
15 be inventoried for possible later sale at that width, or at
16 narrower widths after further slitting.

17 *EN. 057* FIGS. 4 to 6 illustrate the novel tape stock and tape
18 of the invention in greater detail. FIG. 4 is a cross-
19 sectional view, partly broken, taken on plane 4-4 of FIG. 2
20 and inverted 180 degrees. The easier or lower release coating
21 33 and higher or harder release coating 35 are shown. FIG.
22 5 is a cross section of the slit individual tape which is
23 self-wound into the roll 41. FIG. 6 shows two adjacent wraps
24 or turns of the roll 42. While these figures are not to
25 scale, they do give a rough idea of the insignificant effect
26 of the printed adhesive-inhibiting masking 36 on the overall
27 thickness of the tape. As suggested in FIGS. 4-6, the tapes
28 are substantially uniform in thickness from edge to edge.
29 Actual typical thicknesses which have been used are, for
30 example, (microns): substrate 120, adhesive layer 30, release
31 coats (each) 1, ink or masking 0.4.

32 As particularly suggested by FIG. 6, the edge portions
33 of the tape rolls are substantially as tightly wound as the
34 center portions, with firm layer-to-layer support between the
35 various turns of the roll out to the very edges of the roll.
36 *EN. 06* Converters of tapes and other products using the printed

1 adhesive masking of the present invention can handle the
2 adhesive tapes or stocks efficiently. The rolls can be
3 tightly wound. There is little or no cutting differential
4 between masked and unmasked adhesive areas. The rolls unwind
5 in a uniform manner. The risk of edge damage (nicking) of the
6 rolls is reduced.

7 As described above, in the foregoing examples of the
8 invention, the printing of the adhesive barrier is along a
9 continuous zone or line, and the tape is formed in whole or
10 in part by slitting along that continuous line through the
11 tape substrate, an adhesive coating, and the printed barrier.

12 *Ans. a7* Various adhesives have been used in transfer coating in
13 the past as illustrated in FIG. 1, and in general any such
14 adhesive can be adapted to the invention. For example, the
15 adhesive may be a thermally cross-linked acrylic adhesive, the
16 cross-linking mechanism comprising a metal chelate such as
17 aluminum acetylacetonate (in a small weight percentage, say
18 0.15%).

19 *Ans. a8* A suitable masking for such adhesive may be formed by
20 printing, using as the ink "Flexo Write on White" CLA 40457F
21 supplied by Sun Chemical Corp. The ink may be thinned with
22 a press solvent to a running viscosity of 20-22 seconds as
23 measured using a No. 2 Zahn Cup. The solvent may be a mixture
24 of 75% normal propyl alcohol, 25% ethyl acetate and 5%
25 "Ektosolve" (Chemcentral).

26 *Ans. a9* The following has been used for the lower or easier
27 release coating 33, in weight percentages:

28	Dow Syloff 7044	96.10%
29	Dow Q2-7048	3.90%

30 This coating was applied at 1.5 grams per square meter.

31 *Ans. a10* The following has been used for the higher or harder
32 release coating 35:

33	Dow Syloff 7044	51.00%
34	Dow Q2-7069	44.50%
35	Dow Q2-7048	4.50%

1 This coating was applied at 1.4 grams per square meter.
2 *Ans. A11* A suitable choice for liner in the practice of the
3 invention as above described is 80# "Super Tough" (Otis
4 Paper).

5 Similar practices may be utilized in the manufacture of
6 improved diaper fastener-tab stock adapted to be supplied to
7 a diaper manufacturer and to be separated by the manufacturer
8 into individual diaper-fastening tabs and applied to
9 individual diapers, usually two tabs to a diaper for infants,
10 and two to six for adults.

11 The individual fastener 50 seen in FIG. 9 is, in effect,
12 a cross-sectional view of the diaper fastener stock from which
13 the individual fastener has been formed by transverse cuts.
14 This stock, then, consists of initially flat but flexible
15 first and second substrates 52 and 54 suitable to be formed
16 in long passes along the machine direction (into the paper as
17 viewed in FIGS. 7-9) of a coating and laminating line without
18 the necessity for folding operations and completely by web
19 coating, slitting and web-to-web laminating operations, and
20 suitable for high-speed dispensing on automatic equipment.
21 The substrates may be polypropylene film 4.6 mils in
22 thickness, for example.

23 The first or anchoring substrate 52 bears first substrate
24 adhesive 56 on its underside. The first substrate 52 and the
25 first substrate adhesive 56 extend, transversely to machine
26 direction, along first and second length portions 61 and 62
27 of the web construction, respectively.

28 The second or additional substrate 54 bears second
29 substrate adhesive 58 on its underside and also extends along
30 the first and second length portions 61 and 62. Release means
31 for the adhesive 58 of the second substrate 54 is carried on
32 the first substrate 52 and may be a release coat 64. This
33 release means extends along the second length portion 62 but
34 not significantly along the first length portion.

35 *Ans. A12* The first and second substrate adhesives may have the
36 following formulation:

1	Kraton 1107 (Shell Chemical)	31.7%
2	Escorez 1310LC (Exxon Chemical)	46.3%
3	Wingtack 10 (Goodyear Chemical)	19.8%
4	Ethanox 330 (Ethyl Corp.)	1.0%
5	Plastonox LTDP (American Cyanimid)	1.2%

6 *Ans. 113* A suitable masking or barrier may be formed by printing,
7 using as the ink "Suntex 182 Pink" CLA 40457F supplied by Sun
8 Chemical Corp. The ink may be thinned with the same press
9 solvent given previously, to the same running viscosity.

10 The second substrate construction as seen in FIG. 7 is
11 formed in a manner similar to the formation of the tape seen
12 in FIG. 5. The substrate 54 is formed from a substrate twice
13 as wide by slitting after being coated with the adhesive 58
14 and after adhesive barrier means 57 is printed on the adhesive
15 along a continuous zone or line at the midline of the original
16 or unslit substrate.

17 Preferably, the barrier means 57 is an ink or other
18 barrier of a color which contrasts with the color of the
19 adhesive. (If desired, the substrate 54 may be provided at
20 its corresponding edge with corresponding coloring, not shown,
21 which contrasts with the remainder of the substrate. This can
22 be done by known printing or coextrusion techniques. Slitting
23 produces two tapes, mirror images of each other, one of which
24 is the tape seen in FIG. 7, which includes the adhesive
25 masking portion 57.

26 The first substrate portion as seen in FIG. 8 is formed
27 by conventional coating techniques and may also represent a
28 half-width of original substrate stock slit down the middle.
29 The tapes as seen in FIGS. 7 and 8 can be cut from original
30 or unslit substrates which are combined prior to slitting, or
31 can be combined following slitting of the original or unslit
32 substrates. In any event, when the constructions of FIGS. 7
33 and 8 are laminated together to form the diaper fastener stock
34 illustrated in FIG. 9, the masking portion 57 is contained
35 snugly within the associated end of the lamination to provide
36 built-in end tab means.

1 Suitable release means may be provided to allow the
2 construction as so far described to be self-wound for storage
3 and shipment. Such release means may be a release coat 66 on
4 the second substrate 54. When the diaper fastener stock is
5 wound on itself, the first substrate adhesive 56 is releasably
6 supported against the release coat 66, and readily separates
7 therefrom when the roll is subsequently unwound on a diaper
8 manufacturing line.

9 When the diaper fastener stock is wound as just
10 described, the built-in end tab afforded by the masking
11 portion 57 and associated overlying portion of substrate 54
12 allows the roll to form evenly without build-up of one side,
13 and presents evenly thick edges which are supported from one
14 turn to the next in the wound roll.

15 ~~On the manufacturing line, the diaper fastener stock is~~
16 ~~unwound and cut transversely to form a series of individual~~
17 ~~fasteners which are applied, usually in pairs, to individual~~
18 ~~diapers by being folded around a diaper edge. FIG. 10 shows~~
19 ~~an individual fastener cut from the stock described above~~
20 ~~applied around the edge of a diaper 70. This is the~~
21 ~~undeployed condition of the diaper fastener. Fasteners made~~
22 ~~according to the invention have been found to perform~~
23 ~~satisfactorily when applied to Huggies Super Trim diapers~~
24 ~~(Kimberly Clark) which, as is typical of many contemporary~~
25 ~~disposable diaper constructions, have a fastener-receiving~~
26 ~~frontal tape to reinforce the relatively fragile and easily~~
27 ~~torn diaper outer plastic shell or envelope.~~

28 FIG. 11 illustrates the deployed condition of the diaper
29 fastener. When a diaper is applied to an infant or other
30 person, each diaper fastener is moved from undeployed to
31 deployed condition. The second length portion of the second
32 substrate 54 constitutes deployment means separable from the
33 second length portion of the first or anchoring substrate 52
34 for deployment as shown in FIG. 11 and adherence to another
35 portion of the diaper (not shown) by application of the
36 exposed second length portion of the second substrate adhesive

1 58 to such other diaper portion. The end-tab means comprising
2 masking portion 57 is at the free end of such deployment
3 means.

4 In other words, the second substrate 54 will be seen to
5 constitute substrate means which has an inner and an outer
6 end, and which is fastened at its inner end to one part of the
7 diaper via the adhesive layers 56 and 58 and the substrate 52
8 (FIG. 10). The tape will be seen to have a pressure-sensitive
9 adhesive face 59 (FIG. 11) at least at the outer end of such
10 substrate means, such face being carried on release means 64
11 which in turn is carried on the same part of the diaper via
12 the substrate 52 and adhesive 56 (FIG. 10). The second
13 substrate is adapted to have its outer end peeled from and
14 thereby deployed from the part of the diaper seen in FIGS. 10
15 and 11 for fastening to another part of the diaper (not shown)
16 to thereby establish a user joint and fasten the diaper. The
17 outer end of the second substrate has lift tab means in the
18 form of the masking portion 57 for initiating peeling of the
19 outer end from the release means 64.

20 The barrier means or masking portion may, if desired,
21 be provided with fragrances, which may simply be added to a
22 printing ink. Absorbent powders in the ink may function to
23 pick off finger oils of the parent or other caregiver who
24 handles the diaper tab, thereby reducing the likelihood of
25 contamination of the bonding interface established when the
26 tab is fastened. The ingredients of the barrier or masking
27 may have a double function, for example an absorbent powder
28 may contribute both to deactivating or masking the pressure-
29 sensitive adhesive and to absorbing finger oils.

30 *Ins. 9.15* Many variations in the specific example described above
31 are possible. FIG. 12 shows a variant in which the invention
32 is incorporated in a diaper fastener of the general type shown
33 in U.S. Patent 4,020,842 to Richman et al. the disclosure of
34 which is adapted by reference as if fully repeated herein.
35 This type of fastener has more than one additional substrate
36 and correspondingly more than one deployment means. In the

1 construction of FIG. 12, a first or anchoring substrate 52 and
2 a second or additional substrate 54, and associated first and
3 second substrate adhesives 56 and 58, are provided similarly
4 to the construction of FIG. 9. Further, a third substrate 74
5 (constituting a second additional substrate) is provided along
6 with associated third substrate adhesive 76. Since this
7 substrate is the outermost in this construction, a release
8 means such as the release coat 77 is provided along the entire
9 length of the substrate for self-winding purposes. The
10 release coat 66 of the FIG. 9 construction is replaced by
11 shortened release coat 66a which extends along the second
12 length portion corresponding to length portion 62 in FIG. 9,
13 but not significantly along the first length portion
14 corresponding to length portion 61 in FIG. 9. Preferably, the
15 substrate adhesives 58 and 76 are interrupted at the fold-
16 around portion of the diaper fastener by adhesive gaps 58g and
17 76g.

18 The second substrate 54 of the FIG. 12 construction is
19 interrupted by a slit or small gap 72. The general operation
20 of the construction in the manner of deployment, reopening and
21 reclosing is the same as that of the aforesaid Richman et al.
22 patent. However end-tab means of the general kind intended
23 by the present invention is provided on at least one of the
24 deploying substrates. In this case, end-tab means comprising
25 the printed masking portion 57a is provided in association
26 with the free end of substrate 54, and end-tab means
27 comprising the printed masking portion 57b is provided in
28 association with the free end of substrate 74.

29 Still other forms of diaper fasteners utilizing the
30 invention may be provided. Thus a type of two-substrate tab
31 may be provided wherein both substrates perform an anchoring
32 function, and less substrate material is used than in the
33 designs previously described.

34 Such diaper tab stock may be first combined on the diaper
35 manufacturing line from stock components made by different
36 manufacturers. For example the two substrates and associated

1 adhesives and release coats may be provided in self-wound form
2 from different sources or from a single source.

3 Thus as shown in FIGS. 13-17, first and second substrates
4 82 and 84 are provided with first and second substrate
5 adhesives 86 and 88, and release coats 94 and 96 are provided
6 on the first and second substrates. In the industry, the
7 first and second substrates together with associated adhesives
8 and coatings are often referred to respectively as release
9 tape stock and fastener tape stock. The diaper manufacturer
10 combines the release tape stock or substrate 82 and the
11 fastening tape stock or substrate 84 in the manner shown in
12 FIG. 15, then cuts the combined tape stock into individual
13 fastener tapes and applies successive fasteners around a
14 diaper edge in the manner seen in FIG. 16. Fastener tapes for
15 the opposite side edge of the diaper are formed and combined
16 in the mirror image of the illustrated tape.

17 The second substrate 84 will be seen to constitute
18 substrate means which has an inner and an outer end, and which
19 is directly fastened at its inner end to one part of the
20 diaper by the adhesive layer 88. (FIG. 16). The tape will be
21 seen to have a pressure-sensitive adhesive face 89 (FIG. 17)
22 at least at the outer end of such substrate means, such face
23 being carried on release means 94 which in turn is carried on
24 the same part of the diaper via the substrate 82 and adhesive
25 86 (FIG. 16). The second substrate is adapted to have its
26 outer end peeled from and thereby deployed from the part of
27 the diaper seen in FIGS. 16 and 17 for fastening to another
28 part of the diaper (not shown) to thereby establish a user
29 joint and fasten the diaper. The outer end of the second
30 substrate has lift tab means in the form of the masking
31 portion or barrier means 87 for initiating peeling of the
32 outer end from the release means 94.

33 In this construction, the release coat 94 serves two
34 release functions; it allows self-winding of the substrate
35 82 for shipment from the tape stock manufacturer to the diaper
36 manufacturer and it serves as the release face against which

1 the adhesive face 89 is stored in the conditions shown in
2 FIGS. 15 and 16. The release coat 96 performs the single
3 release function; it allows self-winding of the substrate 84
4 for shipment.

5 The various slitting, patterning and combining operations
6 at the fingerlift end of the diaper fastener stock can be
7 performed in duplicate at the web center on a stock
8 manufacturing line, with the slitting, patterning and
9 combining on one lateral side of the infed webs being done
10 in mirror image to the same operations on the other side.
11 In such case, of course, the width of the infed webs is at
12 least double the width of the resulting diaper fastener stock.

13 It is to be noted that in all instances the end-tab means
14 is located within the length of the longest of the one or more
15 additional or deployment substrates.

16 The result is a diaper tab fastener with a fingerlift
17 superior to those of the prior art discussed above. The end-
18 tab means of the invention can be readily and conveniently
19 grasped and manipulated by the person applying the diaper.
20 The end-tab means can be readily fabricated on a diaper
21 fastener stock production line by simple patterning and
22 slitting steps that are fully compatible with economical high
23 speed production. The stock can be self-rolled in smooth,
24 uniform rolls that are free of local high spots and resulting
25 distortions.

26 The invention is not limited to the specific details of
27 the disclosed embodiments, but is defined in the following
28 claims.